

VARNISHING CHECKLIST

At least two days in advance:

- Set the room thermostat to a constant 18-20°C. ☐
- Switch off the underfloor heating or reduce the water temperature at the manifold to 25°C, lowering it by 5°C per day. ☐
- Set up a temperature/hygrometer with memory. Reset the min/max values. ☐
- Check the surface temperature using an infrared thermometer. ☐
- Check that all doors rotate freely without touching the floor. ☐
- Check that the exit is sufficiently sheltered. ☐
- Check that there is sun protection in place. ☐

The day before:

- Deliver the varnish in good time and place it in the room where applied. Do not leave it in the van. ☐
- Check the application and drying conditions – take appropriate measures if there are any deviations. ☐
 - ✓ Room temperature – preferably between 18°C and 22°C and kept constant. ☐
 - ✓ Floor temperature – preferably between 15°C and 22°C. ☐
 - ✓ Relative humidity – preferably between 50 and 70 per cent. ☐
 - ✓ Adequate air circulation and fresh air supply. No draughts across the floor. A fan may be installed if necessary. ☐
 - ✓ Sufficient daylight. ☐
- Check the weather forecast. ☐

On the day itself – before you start varnishing:

- Dampen any direct sunlight if necessary. ☐
- Close the windows, unless ventilation is required. ☐
- Mask off where necessary. ☐
- Clear the surface and immediate surroundings of dust. Prevent dust from blowing in. ☐
- Check and note down the batch numbers ☐
- Clearly mark the surface as 'WET!' and specify how long this applies. ☐
- Block off the entrances to prevent anyone from accidentally walking through. Also bear in mind pets. ☐
- Cover the letterbox. ☐

After varnishing:

- Please observe and communicate the specified drying times. ☐
- Do not cover the surface permanently until the products used have fully cured. Even then: hand over the work first, then cover it to avoid any misunderstandings later on. ☐

Need more information or advice?

For quick answers to frequently asked questions, visit www.rigoverffabriek.nl. For immediate advice during office hours, please call +31 (0)255 548 448, email advies@rigoverffabriek.nl or send a WhatsApp message to +31 (0)6 47 05 78 24. Technical Data Sheet & Safety Data Sheet available at www.rigoverffabriek.nl under the product – documents/information sheets.