

Technical Data Sheet

SKYLT Titanium #5550



Application:

SKYLT Titanium is a water-based two-component product that can be applied to parquet, wooden, cork, concrete look and linoleum floors, among others, for normal to intensive use in houses, offices, shops and public buildings. It is also very suitable for furniture. Intensifies the colour of hardwood and other dark substrates. Always apply a test coat first on unknown substrates. See the SKYLT INSTRUCTIONS for extensive application instructions and a legend of the symbols used. If you have specific questions, feel free to call us or send an app message to 06 – 47 05 78 24.

The values below apply to the ready product. Drying conditions of 20°C, 65% RH and sufficient ventilation are observed as applicable standard.

| Colour | Pale white liquid, dries to clear transparent. Does not yellow. |
|--------------------|---|
| Degree of gloss | Ultra Matt |
| Odour | Mild |
| Solids | ~27% BY VOLUME |
| рН | ~ 8 |
| Consistency | Thin liquid |
| Ease of sanding | Easy |
| Coverage | 8 - 12 m² per litre |
| Dust dry | 1 hour |
| Re-coatable | 3 - 4 hours |
| Light use | 12 hours |
| Intensive use | 3 days (do not cover floor with film or carpets prior to this) |
| Scratch resistance | Very resistant to scratches from normal use, for instance sand under |
| | shoes. |
| Resistance to wear | Very good |
| Resistance | Very good chemical resistance to water, alcohol and detergents. Good resistance to coffee, wine and tea stains. |



Technical Data Sheet

SKYLT Titanium #5550

| Roughness/slip resistance | Prepared for daily use, for foot traffic. |
|------------------------------|--|
| Complies with | AgBB/DiBt – Germany Indoor Air Quality Decree – Belgium |

Available in the following packaging(s):

1 litre bottle; item no. 5529463; EAN 8716544040281 (box = 12 x 1 ltr)
Part A = 0.91 ltr, part B = 0.09 ltr
4 litre can; item no. 5529479; EAN 8716544040298 (box = 4 x 4 ltr)
Part A = 3.64 ltr, part B = 0.36 ltr

See the MATERIAL SAFETY DATA SHEET for safe and healthy working conditions.